

Archetypal Soft-Mode Driven Antipolar Phase Transition in Francisite $\text{Cu}_3\text{Bi}(\text{SeO}_3)_2\text{O}_2\text{Cl}$

Wednesday, 11 September 2019 16:05 (10 minutes)

Antiferroelectricity can be seen as being a property similar to antiferromagnetism with electric dipoles instead of spins. It is characterized by a phase transition between a high- and a low-symmetry phase where antiparallel dipoles emerge [1]. In analogy with soft-mode driven ferroelectric transitions (e.g. in PbTiO_3), it is then possible to think of an ideal antiferroelectric phase transition driven by an “anti-polar soft-mode”, which is a soft phonon mode related to antiparallel ionic displacements [2]. However, such a phase transition has not been observed yet; instead, classical antiferroelectric transitions are usually of the order-disorder type.

In this study, we show that francisite ($\text{Cu}_3\text{Bi}(\text{SeO}_3)_2\text{O}_2\text{Cl}$) undergoes such an anti-polar soft-mode driven phase transition. Francisite is an orthorhombic crystal that has a phase transition from space group Pmmn to Pcmm at 115 K [3]. This phase transition induces a doubling of the unit cell along the c axis, which folds the zone-boundary Z point $(0,0,1/2)$ of the high-symmetry phase onto the Γ point in the antipolar phase [4]. We measured the low-frequency phonon modes in both phases using a combination of Raman spectroscopy, Inelastic X-Ray Scattering (IXS) and Thermal Diffuse Scattering (TDS). IXS and TDS measurements have been performed at the ID 28 beamline of ESRF [5].

Raman spectra across the phase transition are shown on Fig. 1. and show a clear soft phonon mode visible only in the low-temperature phase. The soft-mode above T_c on the other hand is seen in the IXS spectra and in the TDS intensity. Fig. 2 shows the combination of experimental data with the soft-mode energy squared as a function of temperature. It displays a typical soft-mode behaviour in the vicinity of T_c , with deviations originating from mode coupling with other low lying phonon modes. The slopes of E^2 vs. T indicate that the transition is close to tricritical.

Fig. 1 is the enclosed “Raman_cascade.jpg” file and Fig 2. is “Soft-mode_evolution.jpg”

Summary

Topic

1. Multiferroics and ferroelectrics

Primary authors: MILESI-BRAULT, Cosme (Luxembourg Institute of Science and Technology); Dr CONSTABLE, Evan; Dr ARAMBERRI, Hugo (Luxembourg Institute of Science and Technology); Dr SIMONET, Virginie (Institut Néel); DE BRION, Sophie (Institut Néel); Dr BERGER, Helmut (École Polytechnique Fédérale de Lausanne); Dr PAOLASINI, Luigi (ESRF); Dr BOSAK, Alexei (ESRF); INIGUEZ, Jorge (Luxembourg Institute of Science and Technology); Dr GUENNOU, Mael (Physics and Material Science Research Unit, University of Luxembourg)

Presenter: MILESI-BRAULT, Cosme (Luxembourg Institute of Science and Technology)

Session Classification: Afternoon Session 1