

Investigation of high pressure phase transition by means of infrared spectroscopy in the Cairo frustrated pentagonal magnet Bi₂Fe₄O₉

Wednesday, 11 September 2019 11:50 (20 minutes)

Bi₂Fe₄O₉ is a common by-product in the synthesis of the multiferroic compound BiFeO₃ and has been claimed itself to display multiferroic properties [1]. The lattice formed by the two different sites of four iron Fe³⁺ magnetic atoms is quite remarkable as it materializes the first analogue of a magnetic pentagonal lattice [2]. For its peculiar lattice geometry it has attracted interest in the field of geometrical frustration. At room temperature and atmospheric pressure, the crystal structure is orthorhombic within the Pbam space-group and the compounds undergoes a magnetic phase transition at 238 K from a paramagnetic state toward a non collinear magnetic state characterized by a propagation vector $k = (1/2, 1/2, 1/2)$ and a large degree of frustration ($\theta_p/T_N \sim 7$) [2]. Recently it has been shown that Bi₂Fe₄O₉ undergoes a structural transition under pressure at 6-8 GPa toward the maximal non-isomorphic subgroup Pbnm, with $c' = 2c$. The driving force of the phase transition is the displacement of the O1 oxygen atom from fully constrained Wyckoff position 2b to a less-constrained 4c one [3]. Previous studies have reported the investigation of dynamical properties by mean of Raman spectroscopy both at ambient condition and at high pressure in a diamond anvil cell [3,4]. However, the vibrational modes involving O1 oxygen atoms are not Raman active but infrared active.

We will report the first polarized infrared spectroscopy measurement of Bi₂Fe₄O₉ performed in a DAC from 1 to 20 GPa in the far-infrared range [60-800 cm⁻¹] and at low temperature. The measurements have been performed at the AILES beamline of synchrotron SOLEIL exploiting the high-pressure/low-temperature set-up [5] coupled with the high brilliance of the radiation source in a wide spectral range on a very thin sample (~50 μm) placed between diamonds with culets of 500 μm diameter. From our high quality spectra, we are able to identify the B_{3u} and B_{2u} modes within the (ab)-plane. Interestingly, while all phonon frequencies increase with pressure, the phonon mode around 200 cm⁻¹ undergoes an anomalous softening with increasing pressure. In order to assign the phonon modes and reveal the microscopic mechanism of the high-pressure transition we also have performed DFT calculation at different pressures. The calculation mostly accounts for the measured phonon modes allowing the assignation of atomic motions.

[1] A. K. Singh, et al., Applied Physics Letters 92, 132910 (2008).

[2] E. Ressouche, et al., Review Letters 103, (2009).

[3] A. Friedrich, et al., Journal of Physics: Condensed Matter 24, 145401 (2012).

[4] M. N. Iliev, et al., Physical Review B 81, (2010).

[5] A. Voute, et al., Vibrational Spectroscopy 86, 17 (2016).

Summary

Topic

1. Materials under high pressure

Primary author: VERSEILS, Marine (Ligne AILES - Synchrotron SOLEIL)

Co-authors: Dr BEAUVOIS, Ketty (INAC/MEM); Dr LITVINCHUCK, Alexander (5Texas Center for Superconductivity, University of Houston, USA); Dr DEBRION, Sophie (Institut Néel, CNRS&Univ. Grenoble Alpes, Grenoble, France); Dr SIMONET, Virginie (Institut Néel, CNRS&Univ. Grenoble Alpes, Grenoble, France); Dr RESSOUCHE, Eric (INAC/MEM, CEA-Grenoble, France); Prof. SKUMRYEV, Vassil (ICREA, Universitat Autònoma de Barcelona, Bellaterra, Spain); Prof. GOSPODINOV, Marin (Institute of Solid State Physics, Bulgarian Academy of Sciences, Sofia, Bulgaria)

Presenter: VERSEILS, Marine (Ligne AILES - Synchrotron SOLEIL)

Session Classification: Morning Session 2