




MISURE DI LUCCHINI



Problema osservato da Marco Lucchini nella trasmittanza del BSO di SICCAS.

Forte assorbimento nella regione di emissione

MISURE DI SICCAS



Dear Prof.Lucchini,

We measured the transmission of some BSO crystals grown recently, the crystals have the cross section of 15X15mm to 20X20mm, the length varies from 150-200mm, please find below figure of the data.

We observed the absorption at 400nm in 2 samples with yellow precipitates, other samples seem OK.

Please let me know if you need our sample for evaluation, .