14th International Conference on Nuclear Microprobe Technology and Applications



Contribution ID: 40

Type: Poster

P90 - Multiscale characterization of helium migration in transition metal carbides and nitrides

Friday, 11 July 2014 13:00 (1 hour)

Multiscale characterization of helium migration in transition metal carbides and nitrides

S. Agarwal1, P. Trocellier1, H. Khodja2, S. Vaubaillon1,3, D. Brimbal1, S. Miro1

1 CEA, DEN, Service de Recherches de Métallurgie Physique, Laboratoire JANNUS 2 CEA, DSM, IRAMIS, NIMBE, Laboratoire d'Étude des Éléments Légers 3 CEA, INSTN, UEPTN, Laboratoire JANNUS F-91191 Gif-sur-Yvette, France

Transition metal carbides and nitrides exhibit very interesting thermomechanical and radiation tolerance properties and are considered as possible candidate materials for use in advanced nuclear fission and fusion applications. The accumulation of helium mainly produced by neutron induced nuclear reactions (n, \boxtimes) may have detrimental effects on the ageing process of nuclear ceramics such as TiC, ZrC and TiN. A thorough characterization based on quantitative analytical tools needs to be carried out to identify and describe the key mechanisms able to drive helium migration in these compounds. In this paper, we show that combining ion milli- and micro-beam analysis using the nuclear reaction 3He(d, p0)4He together with transmission electron microscopy open the way to obtain quantitative informations on the evolution of the distribution of helium atoms implanted in these compounds after controlled isothermal annealing treatments. The following figures illustrate the behavior of 3He implanted in TiN investigated from the millimeter to the nanometer scale.

3He depth profile measured by milli-NRA in TiN as implanted at 0,27 1016 ions cm-2 and annealed for 2 hours at 1100 or 1500°C. TEM observation of helium bubble distribution in TiN as implanted at 0.27 1016 ions cm-2.

Two dimensional 3He distribution in TiN as implanted at 5.0 1016 ions cm-2 measured by μ NRA. Two dimensional 3He distribution in TiN annealed for 2 hours at 1600°C measured by μ NRA.

Primary authors: Dr TROCELLIER, Patrick (JANNUS Lab., CEA Saclay); Ms AGARWAL, Shradha (JANNUS Lab.)

Co-authors: Dr BRIMBAL, Daniel (JANNUS Lab, CEA Saclay); Dr KHODJA, HICHAM (LEEL, CEA Saclay); Dr MIRO, Sandrine (JANNUS Lab., CEA Saclay); Dr VAUBAILLON, Sylvain (JANNUS Lab. and INSTN, CEA Saclay)

Presenter: Dr TROCELLIER, Patrick (JANNUS Lab., CEA Saclay)

Session Classification: Poster Session with Cheese and Wine